

PRODUCT DATA SHEET

STARSHINE 25

High solids polymer

DESCRIPTION:

STARSHINE 25 is a hard wearing water based copolymer emulsion providing high gloss and slip resistance on stone and vinyl surfaces.

SUGGESTED APPLICATIONS:

STARSHINE 25 is formulated for substrates with a low to medium porosity such as:

- Terrazzo
- Vinyl
- Marble
- Travertine
- Steel floated concrete

CHARACTERISTICS:

STARSHINE 25 is formulated to provide:

- High speed drying, excellent substrate adhesion, easy application
- Colourless on some substrates (test on small area to determine suitability)
- Good gloss & easy maintenance
- Non-slip surface when kept clean and dust free in regular profile
- Low profile

APPLICATION INSTRUCTIONS:

- STARSHINE 25 should be applied using a lambs wool or appropriate synthetic applicator, spreading thinly and evenly over the surface to be coated. Pooling should be avoided.
- For optimal results, burnish between coats with a high speed single disc polisher, using a red or white pad. Coverage, depending on the substrate could be up to 50m per litre². Apply 2-3 coats. Can be used over BASECOAT.

MAINTENANCE:

- STARSHINE 25 should be maintained as and when required.
- Remove daily dirt with a solution of SPECKLEEN® NEUTRADET.
- It is advisable to remove all wet dirt with a wet extraction machine.
- For removal from floor use STARSHINE STRIPPA.

Note: STARSHINE 25 like all polymers, is not a permanent indefinite barrier to contaminants, therefore all spillages etc. should be removed from the substrates surface as soon as possible.

Regular mechanical burnishing enhances the hardness & shine of the product.

STORAGE:

Do not store above 30°C. STARSHINE 25 is classified as non-hazardous. Shelf life is approximately 1 year.

DISPOSAL:

No special requirements however containers should be punctured to avoid them being used for water transportation.

SAFETY:

Harmful if swallowed. No special precautions required when applying. However, the use of rubber or latex gloves and organic vapour

The information in this publication is based on tests that we believe to be reliable. It is the responsibility of the user to ascertain the suitability of the product to the situation since conditions of use are outside of our control and therefore all expressed or implied warranties are confined only to the replacement of product found to be defective upon receipt of goods by purchaser. Written representation for faulty goods must be made to the supplier within 7 days of receipt of product. All products/names are the registered property of SPECKLEEN®

Phone: +27 11 793 3341 Fax: +27 11 793 3342 Mobile: 082 410 6181

E-mail: info@speckleen.co.za | www.speckleen.co.za

4 Retief Place, Northwold, Randburg, Johannesburg, Gauteng, SOUTH AFRICA
P. O. Box 2553 Honeydew, Johannesburg, Gauteng, SOUTH AFRICA, 2040